

**EMSL Analytical, Inc.**

3356 West Catalina Drive Phoenix, AZ 85017

Tel/Fax: (602) 276-4344 / (602) 276-4053

http://www.EMSL.com / phoenixlab@emsl.com

EMSL Order: 122301595

Customer ID: PBSW26

Customer PO:

Project ID:

Attention: Rocky Benard

Preferred Painters/Builders SW Inc

320 W. 21st St

Clovis, NM 88101

Phone: (575) 762-9209

Fax: (575) 762-0689

Received Date: 03/15/2023 9:45 AM

Analysis Date: 03/15/2023

Collected Date: 03/09/2023

Project: CAFB Building 71

**Test Report: Asbestos Analysis of Bulk Materials via AHERA Method 40CFR 763 Subpart E
Appendix E supplemented with EPA 600/R-93/116 using Polarized Light Microscopy**

Sample	Description	Appearance	% Fibrous	Non-Asbestos	Asbestos
				% Non-Fibrous	% Type
#1-Mud 122301595-0001	Office #1 Stucco / Mud	White Non-Fibrous Heterogeneous		20% Ca Carbonate 80% Non-fibrous (Other)	None Detected
#1-Stucco 122301595-0001A	Office #1 Stucco / Mud	Peach Non-Fibrous Homogeneous		100% Non-fibrous (Other)	None Detected
#2-Floor Tile 122301595-0002	Vault Floor Tile And Mastic	Beige Non-Fibrous Homogeneous		97% Non-fibrous (Other)	3% Chrysotile
#2-Mastic 122301595-0002A	Vault Floor Tile And Mastic	Black Non-Fibrous Homogeneous		95% Non-fibrous (Other)	5% Chrysotile
#3 122301595-0003	Lounge Ceiling Texture	White Non-Fibrous Heterogeneous		20% Ca Carbonate 80% Non-fibrous (Other)	None Detected
#4 122301595-0004	Vault-Mastic <i>work area</i>	Black Non-Fibrous Homogeneous		96% Non-fibrous (Other)	4% Chrysotile
#5 122301595-0005	Upper Mechanical Stucco	Peach Non-Fibrous Homogeneous		100% Non-fibrous (Other)	None Detected

Analyst(s)

Nathan Stancik (7)

*Michelle Wilson*Michelle Wilson, Laboratory Manager
or Other Approved Signatory

EMSL maintains liability limited to cost of analysis. Interpretation and use of test results are the responsibility of the client. This report relates only to the samples reported above, and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. The report reflects the samples as received. Results are generated from the field sampling data (sampling volumes and areas, locations, etc.) provided by the client on the Chain of Custody. Samples are within quality control criteria and met method specifications unless otherwise noted. The above analyses were performed in general compliance with Appendix E to Subpart E of 40 CFR (previously EPA 600/M4-82-020 "Interim Method") but augmented with procedures outlined in the 1993 ("final") version of the method. This report must not be used by the client to claim product certification, approval or endorsement by NVLAP, NIST or any agency of the federal government. Non-triable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Estimation of uncertainty is available on request.

Samples analyzed by EMSL Analytical, Inc. Phoenix, AZ NVLAP Lab Code 200811-0, AZ0937, CO AL-19027, CA 2761, TX 300484, HI L-14-004, LA 05113

Initial report from: 03/15/2023 18:49:12